



2025 S. Vandeventer Ave Saint Louis, MO 63110
Phone: 314-773-2000 Fax: 314-786-1300
<http://www.zoneenterprisesusa.com>

PRODUCT INFORMATION

TXSCE3 TANK MAT

Technical Bulletin

DESCRIPTION: Neoprene Blend (Neoprene/EPDM/SBR)

TECHNICAL DATA:

<u>Property</u>	<u>Results</u>	<u>Test Method</u>
Density	7-11 lb/ft ³	ASTM D 1056
Compression Deflection 25%	9-13 psi	ASTM D 1056
Compression Set (MAX)	30%	ASTM D 1056
Water Absorption (MAX)	10%	ASTM D 1056
Tensile Strength*	100 psi	ASTM D 412 (Die A)
Tear Strength*	15 lb/in	ASTM D (Die C)
Elongation*	125%	ASTM D 412 (Die A)
CD Change After Oven Aging	±30%	ASTM D 1056
Resilience*	20%	ASTM D 2632
Flammability Specifications FMVSS-302	Pass	(0.098" Or Thicker)
Service Temperature	-40°F - 200°F	N/A
High Intermittent Temperature	250°F	N/A
Thermal Conductivity	.38 Btu-in/hr-ft ² -°F	N/A

*=Typical

IMPORTANT: The information in this technical bulletin is based on data obtained by our testing and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results obtained from the use thereof, or that any such use will not infringe on any patent. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability for his particular purpose.